



Meade-King, Robinson & Co. Ltd.

Tower Building, 22 Water Street, Liverpool, L3 1BL
Tel: 0151 236 3191, Fax: 0151 236 4431 / 0151 227 1438
Email: chris@mkr.co.uk, Web: www.mkr.co.uk

PRODUCT SPECIFICATION

Description:	MKR 3000 Polyethylene Wax Prills	Issue:	1
		W.325	

Characteristics

Drop Melting Point	D.127	112 – 118°C
Congealing Point	D.938	101 – 107°C
Needle Penetration at 25°C dmm	D.1321	1.9 – 2.1
Needle Penetration at 54°C dmm	D.1321	18.0 – 20.0
Viscosity at 149 °C	D.3236	20 – 40
Colour (visual)		White
Form		Spray cooled prills

NB: This document nullifies and replaces all previous documents referring to this product.